

Nelplas® Protective Wallcovering Test Results—Surface Burning Characteristics

Nelplas 500 Wallcoverings intended for application with the specified adhesive in accordance with instructions accompanying the product.

APPLIED TO INORGANIC REINFORCED CEMENT BOARD

	0.050 In. or Less*	0.060 In. or Less*	0.093 In. or Less*
Flame Spread	25	20	35
Smoke Developed	40	350	350-450
	0.028 In.++	0.50 In. or Less++	
Flame Spread	20	20	N/A
Smoke Developed	140	250	

NELPLAS 600 Wallcoverings intended for application with the specified adhesive in accordance with instructions accompanying the product.

APPLIED TO INORGANIC REINFORCED CEMENT BOARD

	0.060 In. or Less*	0.080 In. or Less*
Flame Spread	20	20
Smoke Developed	130-175	250

* Applied with Minnesota Mining & Manufacturing's "Fastbond 30 or 3M #30 Nonflammable Contact Cement" adhesive at an application rate of 130 sq. ft. per gallon.

++ Applied with Super-Tek Products, Inc.'s "K-Bond" adhesive at an application rate of 80 sq. ft. per gallon.

↓

NELPLAS®

Wall Protection Systems

800-628-0449 • www.nelplas.com • Division 10 26 00